

TEST REPORT

TEST REPORT NUMBER : TURT190049235_REVISED01 **DATE:** 27 March, 2019

APPLICANT: Ünal Kablo San. ve Tic. A.Ş.

ADDRESS: Velimeşe OSB. mah. 247. Sok.NO:4/1 Ergene/Tekirdağ
Tel: 0282 693 30 30 Fax: 0282 693 30 10
Attention : Bahar Koyuncu (baharkoyuncu@unalkablo.com)

SAMPLE DESCRIPTION One sample of PVC,PLUG CABLE,POLYETHYLENE, XLPE, SİLİCON, HFFR, INSULATED AND EXTERIOR SHEATH CABLES

- Sample 1** : One sample of XLPE plastic item
Sample 2 : One sample of SILICON plastic item
Sample 3 : One sample of HFFR plastic item
Sample 4 : One sample of POLYTHENE plasitc item
Sample 5 : One sample of PVC Plug head

DATE IN : 18 March,2019 (08:54)

DATE OUT : 21 March,2019 / 27 March, 2019

REQUEST : In this test report, only Phthalates test was performed according to 2015/863/EU Directive

COUNTRY OF ORIGIN : TURKEY

RESULTS : SEE ATTACHMENT

CONCLUSION : SEE ATTACHMENT

NOTE : In this revised 01 report, Sample description was changed. This report replaced the report no TURT190049235 dated on 21 March, 2019 and must be used instead of it. Report no TURT190049235 dated on 21 March, 2019 is invalid.

"This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid "

"The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory."

PP



Merve AYDOĞAN
Merve Aydoğan
Customer Care Executive



Zeynep Akın
Chemical Laboratory Manager

TEST REPORT

PP



Merve AYDOĞAN
Merve Aydoğın
Customer Care Executive



Zeynep Akın
Chemical Laboratory Manager

(A)TEST RESULT SUMMARY ACCORDING TO IEC 62321

TESTING ITEM	RESULT		
	Sample		
	1	2	3
Cadmium (Cd) Content	NR	NR	NR
Chromium VI (Cr+6) Content (ppm) (for non metal)	NR	NR	NR
Chromium VI (Cr+6) Content (µg/cm ²) (for metal)	NA	NA	NA
Lead (Pb) Content	NR	NR	NR
Mercury (Hg) Content	NR	NR	NR
Flame Retardants			
Polybrominated Biphenyls (PBB)	NR	NR	NR
Monobromobiphenyl (MonoBB)	NR	NR	NR
Dibromobiphenyl (DiBB)	NR	NR	NR
Tribromobiphenyl (TriBB)	NR	NR	NR
Tetrabromobiphenyl (TetraBB)	NR	NR	NR
Pentabromobiphenyl (PentaBB)	NR	NR	NR
Hexabromobiphenyl (HexaBB)	NR	NR	NR
Heptabromobiphenyl (HeptaBB)	NR	NR	NR
Octabromobiphenyl (OctaBB)	NR	NR	NR
Nonabromobiphenyl (NonaBB)	NR	NR	NR
Decabromobiphenyl (DecaBB)	NR	NR	NR
Polybrominated Diphenyl Ethers (PBDE)	NR	NR	NR
Monobromodiphenyl Ether (MonoBDE)	NR	NR	NR
Dibromodiphenyl Ether (DiBDE)	NR	NR	NR
Tribromodiphenyl Ether (TriBDE)	NR	NR	NR
Tetrabromodiphenyl Ether (TetraBDE)	NR	NR	NR
Pentabromodiphenyl Ether (PentaBDE)	NR	NR	NR
Hexabromodiphenyl Ether (HexaBDE)	NR	NR	NR
Heptabromodiphenyl Ether (HeptaBDE)	NR	NR	NR
Octabromodiphenyl Ether (OctaBDE)	NR	NR	NR
Nonabromodiphenyl Ether (NonaBDE)	NR	NR	NR
Decabromodiphenyl Ether (DecaBDE)	NR	NR	NR
Phthalates			
Dibutyl Phthalate (DBP)	ND	ND	ND
Diethyl Hexyl Phthalate (DEHP)	ND	ND	ND
Benzyl Butyl Phthalate (BBP)	ND	ND	ND
Diisobutyl Phthalate (DIBP)	ND	ND	ND

Remarks : ppm=Parts per million based on dry weight of sample
µg/cm²=Microgram per square centimetre
mg/kg with 50 cm²=Milligram per kilogram with 50 square centimetre
ND =Not detected NA =Not applicable NR =Not requested
*=Exceeded Limit

Estimated Total Uncertainty = ((Heavy Metal: ±7% , PBB/PBDE: ±6%, Phthalates: ±6%))

(A)TEST RESULT SUMMARY ACCORDING TO IEC 62321

TESTING ITEM	RESULT	
	Sample	
	4	5
Cadmium (Cd) Content	NR	NR
Chromium VI (Cr+6) Content (ppm) (for non metal)	NR	NR
Chromium VI (Cr+6) Content (µg/cm ²) (for metal)	NA	NA
Lead (Pb) Content	NR	NR
Mercury (Hg) Content	NR	NR
Flame Retardants		
Polybrominated Biphenyls (PBB)	NR	NR
Monobromobiphenyl (MonoBB)	NR	NR
Dibromobiphenyl (DiBB)	NR	NR
Tribromobiphenyl (TriBB)	NR	NR
Tetrabromobiphenyl (TetraBB)	NR	NR
Pentabromobiphenyl (PentaBB)	NR	NR
Hexabromobiphenyl (HexaBB)	NR	NR
Heptabromobiphenyl (HeptaBB)	NR	NR
Octabromobiphenyl (OctaBB)	NR	NR
Nonabromobiphenyl (NonaBB)	NR	NR
Decabromobiphenyl (DecaBB)	NR	NR
Polybrominated Diphenyl Ethers (PBDE)	NR	NR
Monobromodiphenyl Ether (MonoBDE)	NR	NR
Dibromodiphenyl Ether (DiBDE)	NR	NR
Tribromodiphenyl Ether (TriBDE)	NR	NR
Tetrabromodiphenyl Ether (TetraBDE)	NR	NR
Pentabromodiphenyl Ether (PentaBDE)	NR	NR
Hexabromodiphenyl Ether (HexaBDE)	NR	NR
Heptabromodiphenyl Ether (HeptaBDE)	NR	NR
Octabromodiphenyl Ether (OctaBDE)	NR	NR
Nonabromodiphenyl Ether (NonaBDE)	NR	NR
Decabromodiphenyl Ether (DecaBDE)	NR	NR
Phthalates		
Dibutyl Phthalate (DBP)	ND	ND
Diethyl Hexyl Phthalate (DEHP)	ND	ND
Benzyl Butyl Phthalate (BBP)	ND	ND
Diisobutyl Phthalate (DIBP)	ND	ND

Remarks : ppm=Parts per million based on dry weight of sample
 µg/cm²=Microgram per square centimetre
 mg/kg with 50 cm²=Milligram per kilogram with 50 square centimetre
 ND =Not detected NA =Not applicable NR =Not requested
 *=Exceeded Limit

Estimated Total Uncertainty = ((Heavy Metal: ±7% , PBB/PBDE: ±6%, Phthalates: ±6%))

(B) REQUIREMENT:

SUBSTANCE	LIMITS
Cadmium (Cd)Content	0.01 % (100 ppm)
Chromium VI (Cr+6)Content(ppm)(for non metal)	0.1 % (1000 ppm)
Chromium VI (Cr+6)Content($\mu\text{g}/\text{cm}^2$)for metal)	Colorimetric result $< 0.10 \mu\text{g}/\text{cm}^2$ $\geq 0.10 \mu\text{g}/\text{cm}^2$ and $\leq 0.13 \mu\text{g}/\text{cm}^2$ $> 0.13 \mu\text{g}/\text{cm}^2$ Qualitative Result Negative Inconclusive Positive
Lead (Pb) Content	0.1 % (1000 ppm)
Mercury (Hg) Content	0.1 % (1000 ppm)
Flame Retardants	0.1 % (1000 ppm)
Dibutyl Phthalate (DBP)	0.1 % (1000 ppm)
Diethyl Hexyl Phthalate (DEHP)	0.1 % (1000 ppm)
Benzyl Butyl Phthalate (BBP)	0.1 % (1000 ppm)
Diisobutyl Phthalate (DIBP)	0.1 % (1000 ppm)

(C) TEST METHOD :

Testing Item	Testing Method	Reporting Limit
Cadmium (Cd)Content	With reference to IEC 62321-5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic : 2.5 ppm, Metal : 5 ppm, Ceramic : 1.25 ppm
Lead (Pb)Content	With reference to IEC 62321-5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic : 5 ppm, Metal : 10 ppm, Ceramic : 2.5 ppm
Mercury (Hg)Content	With reference to IEC 62321-4:2017,by microwave or acid digestion and determined by ICP-OES	Plastic : 5 ppm, Metal : 10 ppm, Ceramic : 2.5 ppm
Chromium VI (Cr6+) (For non-metal)	With reference to IEC 62321-7-2:2017,by alkaline digestion and determined by UV-VIS spectrophotometer	Plastic : 25 ppm (PVC based) /8.33 ppm (other), Ceramic : 8.33 ppm
Chromium VI (Cr6+) (For metal)	With reference to IEC 62321-7-1:2015 ,by boiling water extraction and determined by UV-VIS spectrophotometer	0.1 mg/kg with 50 cm ² (IN TESTING SOLUTION)
PBBs/PBDEs	With reference to IEC 62321-6:2015,by solvent extraction and determined by GC/MS and HPLC	5 ppm
Phthalates	With reference to IEC 62321-8 (111/321/CD), by solvent extraction and determined by GC-MS.	50 ppm

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com

Sample 1



Sample 2



Sample 3



Sample 4



Sample 5



END OF TEST REPORT

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com